

FLAMMABILITY TEST REPORT

Report No.: LEHTX00914756 **Date Received:** 11/10/16 **Date Tested:** 19/10/16 **Date Issued:** 20/10/16
& 20/10/16

Company Name & Address: DAN MEDICA SOUTH LTD
28 DOWNSVIEW AVENUE
STORRINGTON
PULBOROUGH
WEST SUSSEX
RH20 4PS

Contact Name: LYNNE TIMM

Sample Details

Reference No.: Not stated
Order No.: Not stated
Style No.: TEM
Batch No.: 1
Quality: Not stated
Colour: Blue
Supplier: Dan Medica South Ltd
Intended use: Acute hospital mattress overlay
Quoted fibre composition: Polyester
Retailer: Not stated
Buying Division: Not stated
Sample description: Blue and white coloured woven fabric
White coloured mesh inner
White coloured knitted fabric
Cream coloured knitted fabric
Cream coloured knitted fabric
White coloured mesh inner
Cream coloured knitted fabric
Blue and white coloured woven fabric
White coloured mesh inner
White coloured knitted fabric
Blue and white coloured woven fabric
White coloured mesh inner
White coloured knitted fabric

BS 7177: 2008 + A1: 2011 Specification for resistance to ignition of mattresses, mattress pads, divans and bed bases		
	Requirement	
Clause 4 Performance requirements for resistance to ignition	Medium Hazard	PASS
Clause 5 Sampling and frequency of testing (as Annex A)	See below	N/A
Based on the results achieved the sample tested meets the performance requirements for resistance to ignition as detailed in the Domestic use (Medium Hazard) category of Table 1 in Clause 4 of BS 7177: 2008 + A1: 2011		

Please note: To claim compliance with Clause 5 (Sampling and frequency of testing) mattresses and their filling materials shall be tested as detailed in the table below

Number of units produced per month	More than 2400	Between 400 and 2400	Less than 400
Number of units tested	1 per month	1 per 2400 units	1 every 6 months



.....
STEVEN OWEN
(Chemical Technologist)

.....
ANDREW HALLETT
(Flammability Team Leader)

.....
CAROLE SPOWART
(Flammability Technician)

.....
SIMON CHEE
(Operations Manager)

FLAMMABILITY TEST REPORT

Test Specification

Test Method: BS EN 597-1: 1995 and BS EN 597-2: 1995 as required by
BS 7177: 2008 + A1: 2011 Low Hazard
Ignition Source: BS EN 597-1: 1995: Filterless cigarette.
BS EN 597-2: 1995: Butane Gas flowing at 45 ± 2 ml/min @ 25°C for 15 ± 1 seconds

Conditioning

Prior to Testing: At least 16 hours in an atmosphere having a temperature of $23\pm 2^{\circ}\text{C}$ and a relative humidity of $50\pm 5\%$
At Time of Testing: Temperature between 15°C & 30°C . Relative humidity between 15% & 80%

Pre-treatment / Durability procedure

None

FLAMMABILITY TEST REPORT

Test Results (Top of Mattress)

BS EN 597-1: 1995 Smouldering cigarette

Test number / position	1 (Upper surface of mattress)		2 (Upper surface of mattress)				1 (Tape edge)		2 (Tape edge)	
Criterion of ignition										
Smouldering Criteria										
Unsafe escalating combustion	No		No				No		No	
Test assembly consumed	No		No				No		No	
Smoulders through thickness	No		No				No		No	
Smoulders more than 1 hour	No		No				No		No	
More than 50mm from source	No		No				No		No	
Flaming criteria										
Occurrence of flames	No		No				No		No	
Comments										
Flaming ceased	-		-				-		-	
Sample glowing ceased	-		-				-		-	
Smoke ceased	< 18 Minutes		< 18 Minutes				< 18 Minutes		< 18 Minutes	
Extent of damage (mm) Width / Length	12	63	10	62			11	62	12	64
Result (Ignition/Non Ignition)	Non Ignition		Non Ignition				Non Ignition		Non Ignition	
<i>The above test results relate only to the ignitability of the combination of the materials under the particular conditions of test: they are not intended as a means of assessing the full potential fire hazard of the mattress, mattress pad or upholstered bed base in use.</i>										

BS EN 597-2:1995 (Match Equivalent).

Test number / position	1 (Upper surface of mattress)		2 (Upper surface of mattress)				1 (Tape edge)		2 (Tape edge)	
Criterion of ignition										
Smouldering Criteria										
Unsafe escalating combustion	No		No				No		No	
Test assembly consumed	No		No				No		No	
Smoulders through thickness	No		No				No		No	
Smoulders more than 1 hour	No		No				No		No	
More than 50mm from source	No		No				No		No	
Flaming criteria										
Test assembly consumed	No		No				No		No	
Unsafe escalating combustion	No		No				No		No	
Burning through thickness or to the extremities	No		No				No		No	
Flaming for more than 120 seconds	No		No				No		No	
Comments										
Flaming ceased	0 Seconds		0 Seconds				0 Seconds		0 Seconds	
Sample glow ceased	-		-				-		-	
Smoke ceased	2 Seconds		2 Seconds				3 Seconds		3 Seconds	
Extent of damage (mm) Width / Length	27	14	16	14			25	17	25	17
Result (Ignition/Non Ignition)	Non Ignition		Non Ignition				Non Ignition		Non Ignition	
<i>The above test results relate only to the ignitability of the combination of the materials under the particular conditions of test: they are not intended as a means of assessing the full potential fire hazard of the mattress, mattress pad or upholstered bed base in use.</i>										

FLAMMABILITY TEST REPORT

Test Results (Bottom of Mattress)

BS EN 597-1: 1995 Smouldering cigarette

Test number / position	1 (Upper surface of mattress)		2 (Upper surface of mattress)		1 (Tape edge)		2 (Tape edge)			
Criterion of ignition										
Smouldering Criteria										
Unsafe escalating combustion	No		No		No		No			
Test assembly consumed	No		No		No		No			
Smoulders through thickness	No		No		No		No			
Smoulders more than 1 hour	No		No		No		No			
More than 50mm from source	No		No		No		No			
Flaming criteria										
Occurrence of flames	No		No		No		No			
Comments										
Flaming ceased	-		-		-		-			
Sample glowing ceased	-		-		-		-			
Smoke ceased	< 18 Minutes		< 18 Minutes		< 18 Minutes		< 18 Minutes			
Extent of damage (mm) Width / Length	12	64	10	64			12	62	12	62
Result (Ignition/Non Ignition)	Non Ignition		Non Ignition				Non Ignition		Non Ignition	
<i>The above test results relate only to the ignitability of the combination of the materials under the particular conditions of test: they are not intended as a means of assessing the full potential fire hazard of the mattress, mattress pad or upholstered bed base in use.</i>										

BS EN 597-2:1995 (Match Equivalent).

Test number / position	1 (Upper surface of mattress)		2 (Upper surface of mattress)		1 (Tape edge)		2 (Tape edge)			
Criterion of ignition										
Smouldering Criteria										
Unsafe escalating combustion	No		No		No		No			
Test assembly consumed	No		No		No		No			
Smoulders through thickness	No		No		No		No			
Smoulders more than 1 hour	No		No		No		No			
More than 50mm from source	No		No		No		No			
Flaming criteria										
Test assembly consumed	No		No		No		No			
Unsafe escalating combustion	No		No		No		No			
Burning through thickness or to the extremities	No		No		No		No			
Flaming for more than 120 seconds	No		No		No		No			
Comments										
Flaming ceased	0 Seconds		0 Seconds		0 Seconds		0 Seconds			
Sample glow ceased	-		-		-		-			
Smoke ceased	2 Seconds		2 Seconds		2 Seconds		2 Seconds			
Extent of damage (mm) Width / Length	18	14	17	15			30	25	24	20
Result (Ignition/Non Ignition)	Non Ignition		Non Ignition				Non Ignition		Non Ignition	
<i>The above test results relate only to the ignitability of the combination of the materials under the particular conditions of test: they are not intended as a means of assessing the full potential fire hazard of the mattress, mattress pad or upholstered bed base in use.</i>										

FLAMMABILITY TEST REPORT

Test Specification

Test Method: BS 6807: 2006 Clause 9: (Ignition source 5) as required by
BS 7177: 2008 + A1: 2011 Medium Hazard
Ignition Source: BS 6807: 2006 Source 5: Pine wood crib size 5

Pre-treatment / Durability procedure

None

Conditioning

Prior to testing: At least 16 hours in an atmosphere having a temperature of $23\pm 2^{\circ}\text{C}$ and a relative humidity of $50\pm 5\%$
At time of testing: Temperature between 10°C & 30°C . Relative humidity between 15% & 80%

FLAMMABILITY TEST REPORT

Test Results

Ignition source 5 placed at position 5T (on top of the specimen)

Test Number	1		2	
Criterion of ignition				
Smouldering Criteria				
Unsafe escalating combustion	No		No	
Test assembly consumed	No		No	
Smoulders through thickness	No		No	
Smoulders more than 1 hour	No		No	
More than 100mm from source	No		No	
Flaming criteria				
Test assembly consumed	No		No	
Burning through thickness or to the extremities	No		No	
Flaming for more than 10 minutes	No		No	
Flaming debris causing isolated floor fire	No		No	
Comments				
Flaming ceased	3 Minutes	27 Seconds	4 Minutes	13 Seconds
Smoke ceased	5 Minutes	47 Seconds	7 Minutes	32 Seconds
Extent of damage in mm (Length / Width)	100	95	95	95
Result (Ignition/Non Ignition)	Non Ignition		Non Ignition	
<i>The above test results relate only to the ignitability of the combination of the materials under the particular conditions of test: they are not intended as a means of assessing the full potential fire hazard of the mattress, mattress pad or upholstered bed base in use.</i>				

Ignition source 5 placed at position 5T (below the specimen)

Test Number	1		2	
Criterion of ignition				
Smouldering Criteria				
Unsafe escalating combustion	No		No	
Test assembly consumed	No		No	
Smoulders through thickness	No		No	
Smoulders more than 1 hour	No		No	
More than 100mm from source	No		No	
Flaming criteria				
Test assembly consumed	No		No	
Burning through thickness or to the extremities	No		No	
Flaming for more than 10 minutes	No		No	
Flaming debris causing isolated floor fire	No		No	
Comments				
Flaming ceased	3 Minutes	40 Seconds	4 Minutes	0 Seconds
Smoke ceased	6 Minutes	36 Seconds	7 Minutes	03 Seconds
Extent of damage in mm (Length / Width)	125	185	125	215
Result (Ignition/Non Ignition)	Non Ignition		Non Ignition	
<i>The above test results relate only to the ignitability of the combination of the materials under the particular conditions of test: they are not intended as a means of assessing the full potential fire hazard of the mattress, mattress pad or upholstered bed base in use.</i>				

Conclusions

The sample meets the requirements of BS EN 597-1:1995 (Smouldering cigarette) **PASS**.

The sample meets the requirements of BS EN 597-2:1995 (Match equivalent) **PASS**.

The sample meets the requirements of BS 6807: 2006 Clause 9 (Ignition source 5). **PASS**

The sample meets the flammability performance requirements of BS 7177: 2008 + A1: 2011 Medium Hazard. **PASS**.

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.